

THERMOBEL
VALEURS ACOUSTIQUES


YOUR REFERENCE IN INSULATING GLAZING | BY AGC

	Valeurs acoustiques (EN ISO 717-1) (dB)			Epaisseur (mm)	Poids/m ² (kg)
	Rw	Rw+C	Rw+Ctr		
THERMOBEL					
4 - 16 - 4	30	29	26	24	20
6 - 15 - 4	36	35	31	25	25
8 - 16 - 4	37	35	32	28	30
10 - 15 - 6	38	37	34	31	40
THERMOBEL STRATOBEL					
4 - 16 - 44.2	37	35	31	29	31
44.2 - 16 - 33.2	39	38	34	32	37
6 - 15 - 55.2	39	38	35	32	41
8 - 15 - 55.2	41	39	37	34	46
66.2 - 16 - 55.2	42	41	38	40	57
88.2 - 15 - 66.2	46	45	41	45	72
THERMOBEL STRATOPHONE					
4 - 15 - 44.2 st	39	37	34	28	31
6 - 16 - 44.2 st	41	39	35	31	36
8 - 16 - 44.2 st	42	40	36	33	41
6 - 15 - 66.2 st	42	41	37	34	46
8 - 15 - 66.2 st	43	41	39	36	51
10 - 16 - 44.2 st	45	43	39	35	46
10 - 16 - 55.2 st	46	44	40	37	51
10 - 16 - 66.2 st	46	44	41	39	56
66.2 st - 16 - 44.2 st	49	46	41	38	52
88.2 st - 15 - 44.2 st	50	48	43	41	62
66.2 st - 16 - 66.2 st	50	48	43	42	62
88.2 st - 16 - 66.2 st	52	51	47	46	72
THERMOBEL TG					
4 - 12 - 4 - 12 - 4	33	31	27	36	30
6 - 12 - 6 - 12 - 6	35	33	29	42	45
4 - 15 - 4 - 15 - 6	36	34	29	44	35
4 - 12 - 4 - 12 - 8	37	36	31	40	40
6 - 12 - 4 - 12 - 8	39	37	34	42	45
THERMOBEL TG STRATOBEL					
4 - 12 - 4 - 12 - 33.2	36	35	30	39	36
6 - 16 - 4 - 16 - 44.2	39	37	32	51	46
8 - 16 - 6 - 16 - 33.2	39	38	33	53	51
44.2 - 12 - 6 - 12 - 44.2	41	39	33	48	57
8 - 16 - 4 - 16 - 55.2	41	39	37	55	56
8 - 16 - 6 - 16 - 55.2	43	41	39	57	61
66.2 - 16 - 6 - 16 - 44.2	44	43	39	60	67
THERMOBEL TG STRATOPHONE					
4 - 12 - 4 - 12 - 44.2 st	39	37	32	41	41
6 - 12 - 4 - 12 - 44.2 st	41	39	33	43	46
8 - 12 - 4 - 12 - 44.2 st	42	40	35	45	51
44.2 - 12 - 4 - 12 - 44.2 st	43	41	36	46	52
10 - 12 - 4 - 12 - 44.2 st	44	42	37	47	56
8 - 16 - 6 - 16 - 55.2 st	45	44	40	57	61
10 - 16 - 6 - 16 - 55.2 st	46	44	41	59	66
10 - 16 - 6 - 16 - 66.2 st	47	46	43	61	71
44.2 st - 10 - 4 - 10 - 66.2 st	47	46	40	46	62
44.2 st - 12 - 6 - 12 - 66.2 st	48	46	41	52	67
88.2 st - 12 - 6 - 12 - 66.2 st	51	50	46	60	87